



LIST OF COMPATIBLE SEALANTS WITH THIOVER,

Fenzi North America
11 Dansk Court
Toronto, Ontario

HOTVER A+ AND BUTYLVVER

Phone: 416-674-3831
Fax: 416-674-9323

	SEALANT	Base	Curing	Date of Test	Type of Approval
Alcoa	Reynoplast, black	Polyurethan 1K	neutral	1st quarter 09	Compatible
Alcoa	Reynoplast, grey	Polyurethan 1K	neutral	1st quarter 09	Compatible
Adfast Corp	Adseal Structural 4943	Silicone - Black	Neutral	4th quarter 11	Compatible
Adfast Corp	Adseal 4552	Silicone - White	Neutral	4th quarter 11	Compatible
Adfast Corp	Adseal 4585	Silicone - blanc glacier	neutral	4th quarter 11	Compatible
Adfast Corp	Adseal 4551	Silicone	neutral	2nd quarter 11	Compatible
Adfast Corp	Adseal premium quality	Silicone	neutral	3rd quarter 14	Compatible
Adfast Corp	Adsil RTV silicone	Silicone	neutral	3rd quarter 14	Compatible
Adfast Corp	Adseal Construction	Silicone	neutral	3rd quarter 14	Compatible
Alcoa	Reynoplast, white	Polyurethan 1K	neutral	1st quarter 09	Compatible
Arbo	Arbo Sil LM, translucent	Silicone	neutral		Compatible
Berner	Berner L1, transparent	Silicone alkoxy	neutral	3rd quarter 09	Compatible
Bloem	Easyseal Plus, brown 8007	Silicone alkoxy	neutral		Compatible
Bloem	Easyseal-Plus, white	terpolymer rubber			Compatible
Bloem	Oneseal, white	MS polymer	neutral		Compatible
Bondflex	Sil 199, black	Silicone	neutral	2nd quarter 10	Compatible
Bostik	2685	Silicone	Neutral		Compatible
Chemetall	Naftosil M187	Polysulfide			Compatible
CR Laurence	Butyl 777	Butyl			Compatible
CR Laurence	Butyl rubber sealant, grey	Kautschuk 1K	neutral	2nd quarter 10	Compatible
CR Laurence	Silicone 33S	Silicone	Acetox	4th quarter 11	Incompatible
CR Laurence	Polyurethane , white	Polyurethan 1K	neutral	2nd quarter 10	Compatible
CR Laurence	RTV silicone	Silicone	neutral	2nd quarter 12	Compatible
CR Laurence	Butyl Rubber Sealant 777	Butyl		3rd quarter 10	Compatible
Dap	Alex plus	Silicone	Neutral	1st quarter 16	Compatible
Dekalin	Dekaseal 8936, black				Compatible
Den Braven Zwaluv	Pyropol, grey	Silicone			Compatible
Den Braven Zwaluv	Silicone-BB, white	Silicone			Compatible
Den Braven Zwaluv	Superseal, white	Silicone			Compatible
Den Braven Zwaluv	Window seal plus, white	Silicone	butanone-oxime		Compatible
DL Chemicals	Parabond, white	Hybrid Polymer	moisture		Compatible
DL Chemicals	Varioseal	Hybrid Polymer			Compatible
DL Chemicals	Varioseal Donker	Silicone	butanone-oxime		Compatible
DL Chemicals	Varioseal, creme	Silicone			Compatible
DL Chemicals	Varioseal, grey	Silicone	butanone-oxime		Compatible
DL Chemicals	Varioseal, light brown	Silicone	butanone-oxime		Compatible
Dow Corning	DC 733	Silicone	acetic	3rd quarter 07	Incompatible
Dow Corning	DC 982	Silicone	Neutral	1st quarter 11	Compatible
Dow Corning	688, black	Silicone	neutral		Compatible
Dow Corning	795, black	Silicone	neutral		Compatible
Dow Corning	Contractor weather proofing	Silicone	Neutral	1st quarter '13	Compatible
Dow Corning	DC 1199, white	Silicone	neutral	2nd quarter 15	Compatible
Dow Corning	DC 3362, black	Silicone	2K, neutral		Compatible
Dow Corning	DC 3540, black	Silicone	neutral		Compatible
Dow Corning	DC 3793, black	Silicone	neutral		Compatible
Dow Corning	DC 756 SMS, white	Hybrid Polymer			Compatible
Dow Corning	DC 757	Hybrid Polymer	neutral	4th quarter 09	Compatible
Dow Corning	DC 791	Silicone	Neutral		Compatible
Dow Corning	DC 791, black	Silicone	neutral		Compatible
Dow Corning	DC 791, grey	Silicone	neutral		Compatible
Dow Corning	DC 791, white	Silicone	neutral		Compatible
Dow Corning	DC 794F, black	Silicone	neutral		Compatible
Dow Corning	DC 794F, transparent	Silicone	neutral		Compatible
Dow Corning	DC 794F, transparent white	Silicone alkoxy	neutral	4th quarter 09	Compatible
Dow Corning	DC 794F, white	Silicone	neutral	4th quarter 09	Compatible
Dow Corning	DC 794S	Silicone	Neutral		Compatible
Dow Corning	DC 796	Silicone	Neutral		Compatible
Dow Corning	DC 796, grey	Silicone	neutral		Compatible
Dow Corning	DC 797	Silicone	Neutral		Compatible
Dow Corning	DC 797, black	Silicone	neutral		Compatible
Dow Corning	DC 797, black	Silicone	neutral		Compatible

" The Sealants have been conditioned for 4 weeks per the Rossenheim IFT Method. Fenzi formally advises its customers to use only "approved" products. It should be noted, however, that this list represents product combinations that have been successfully tested at one particular point in time. Fenzi can in no manner be held responsible for a possible change in chemical composition of a prior approved product made by another company. Fenzi regular customers can request compatibility tests at any time, service is free of charge."



LIST OF COMPATIBLE SEALANTS WITH THIOVER,

Fenzi North America
11 Dansk Court
Toronto, Ontario

HOTVER A+ AND BUTYLVVER

Phone: 416-674-3831
Fax: 416-674-9323

Dow Corning	DC 819	Silicone	Neutral		Compatible
Dow Corning	DC 895	Silicone	Neutral		Compatible
Dow Corning	DC 993	Silicone	Neutral		Compatible
Dow Corning	DC 993, black	Silicone	2K, neutral		Compatible
Dow Corning	DC 994, black	silicone	2K		Compatible
Dow Corning	DC 995, black	Silicone	neutral	1st quarter 08	Compatible
Dow Corning	W15 LM, transparent white				Compatible
Drywood Coatings	Soudaseal 220 SP	Hybrid Polymer	Neutral		Compatible
ECl	Emcepren 200, black	Polyurethan 2K	2K		Compatible
Ego	Egoflott, grey				Compatible
Ego	Egosil 300, transparent	Silicone	neutral		Compatible
Ego	Egosil 333, black	Silicone	neutral		Compatible
Ego	Egosil 351, grey	Silicone	neutral		Compatible
Ego	Egosil 360	Silicone	Neutral		Compatible
Ego	Egosil 360, brown	Silicone	neutral		Compatible
Ego	Egosil 630	Silicone	Neutral		Compatible
Ego	Egosilicon 300	Silicone	Neutral		Compatible
Emfi	Emfimatic PMS 60, white	MS hybrid polymer	neutral		Compatible
Everbuild	Premium + 450, white	Silicone	neutral		Compatible
Everbuild	Stixall, crystal clear	Hybrid Polymer	neutral	2nd quarter 09	Compatible
Everlast	W 8000, transparent	Silicone	neutral		Compatible
F.lil Zucchini	MS Super, black	MS polymer	neutral		Compatible
Falcone	Falcohybrid, black	MS hybrid polymer	neutral		Compatible
Fosroc	Secolastic MS55, grey	Modified Silicone	neutral		Compatible
GE	Max Extra	Silicone	Neutral	1st quarter 16	Compatible
GE Silicones	Contractors SCS1000	Silicone	Acetoxy	2nd quarter 08	Incompatible
GE Silicones	SCS1000, Clear	Silicone	Acetoxy	3rd quarter 09	Incompatible
GE Silicones	Contractors SCS1800, Clear	Silicone	Neutral	1st quarter '11	Compatible
GE Silicones	SCS2800 SilGlaze II	Silicone	neutral	1st quarter '12	Compatible
GE Silicones	GE XST eXtreme	Silicone		3rd quarter 09	Compatible
GE Silicones	SCS2000 Silpruf, white	Silicone	neutral		Compatible
GE Silicones	SCS2000, Black	Silicone	neutral	2nd quarter 12	Compatible
Gyso	Polyflex 444, black	MS polymer	neutral		Compatible
H.B. Fuller	PIB 969	Polyisobutylene	none		Compatible
H.B. Fuller	PS-998R, black	Polysulfide 2K	2K		Compatible
Henkel - Teroson	Terostat 158 TS 158, black	hybrid polymer	neutral		Compatible
Henkel - Teroson	Terostat 64	Silicone	Neutral		Compatible
Henkel - Teroson	Terostat MS 930, white	MS Polymer			Compatible
Henkel - Teroson	Terostat MS 935, white	MS polymer	neutral		Compatible
Henkel - Teroson	Terostat MS 939, black	MS hybrid polymer	neutral		Compatible
Henkel - Teroson	Terostat MS 939, grey	MS hybrid polymer	neutral		Compatible
Hercuseal	Glazeseal P+, white	MS alkyd	neutral		Compatible
IGK	IGK 130, black	Polyurethan 2K	2K		Compatible
Illbruck	Perennator FA 101, black	Silicone	neutral		Compatible
Illbruck	Perennator SF 141	Silicone	Neutral		Compatible
Kawo	2K-Reparaturkitt, dark brown	Alkyd resin	2K		Compatible
Kawo	Elastokitt, white	Syil Mod. Polymer	neutral		Compatible
Kawo	Kawo DB89, grey	Silicone	neutral		Compatible
Kawo	Kawo SG64	Silicone	Neutral		Compatible
Kawo	Kawo SG64, black	Silicone	neutral		Compatible
Kawo	Kawo SL 54, transparent	Silicone	neutral		Compatible
Kawo	SG 64, black	silicone	neutral		Compatible
Kawo	SL 55, brown	Silicone	neutral		Compatible
Kawo	SL 55, white	Silicone	neutral		Compatible
Kawo	TK 61, black	Polysulfide 1K			Compatible
Koemmerling	GD 115	Polyisobutylene	none		Compatible
Koemmerling	GD 826 N, black	Silicone alkoxy	neutral		Compatible
Koemmerling	Koediglaze P, grey	Polyurethan 2K	2K		Compatible
Koemmerling	Koedisil	Silicone			Compatible
Koemmerling	Koedisil A, transparent	Silicone	neutral		Compatible
Koemmerling	Koedisil A, white	Silicone	neutral		Compatible
Koemmerling	Koedisil GD 823N, black				Compatible

" The Sealants have been conditioned for 4 weeks per the Rossenheim IFT Method. Fenzi formally advises its customers to use only "approved" products. It should be noted, however, that this list represents product combinations that have been successfully tested at one particular point in time. Fenzi can in no manner be held responsible for a possible change in chemical composition of a prior approved product made by another company. Fenzi regular customers can request compatibility tests at any time, service is free of charge."



LIST OF COMPATIBLE SEALANTS WITH THIOVER,

Fenzi North America
11 Dansk Court
Toronto, Ontario

HOTVER A+ AND BUTYLVVER

Phone: 416-674-3831
Fax: 416-674-9323

Koemmerling	Koedisil, transparent	Silicone			Compatible
Koemmerling	PS 200, black	Polysulfide 2K	2K		Compatible
Maderag AG	Record OX2, black	Silicone	oxime		Compatible
Manus Products	Manus Bond 75-AM	Proprietary		1st quarter '11	Compatible
Merz+Benteli AG	Gomastit VG27, black	MS hybrid polymer			Compatible
Merz+Benteli AG	Gomastit VG30, black	MS hybrid polymer			Compatible
Mulco	Mulco Supra Expert	Silicone	Acetoxo	2nd quarter 15	Compatible
Mulco	Supra Expert Thermoplastic	Rubber based	Neutral	4th Quarter '14	Compatible
Mulco	Mulco PVC translucent	Silicone		2nd Quarter 15	Compatible
Novagard	Novaflex silicone	Silicone		1st quarter 14	Compatible
Novatech	TEC7, black	Blended Polymer	neutral		Compatible
Novatech	TEC7, grey	Blended Polymer	neutral		Compatible
Novatech	TEC7, white	Blended Polymer	neutral		Compatible
NPC	Solar Seal 900	Terpolymer rubber	solvent	3rd quarter 07	Incompatible
NPT	Eco Simp, grey	Sylil Mod. Polymer	moisture		Compatible
Otto Chemie	Novasil S10	Silicone	Neutral		Compatible
Otto Chemie	Novasil S7	Silicone	Neutral		Compatible
Otto Chemie	Novasil S94, black	Silicone	butanone-oxime		Compatible
Otto Chemie	Ottoseal S120, brown	Silicone alkoxy	neutral		Compatible
Otto Chemie	Ottoseal S7, grey	Silicone	neutral		Compatible
Otto Chemie	Ottoseal S94, black	Silicone	butanone-oxime		Compatible
Otto Chemie	Ottoseal S94, grey	Silicone	butanone-oxime		Compatible
Otto Chemie	Ottoseal S94, white	Silicone	butanone-oxime		Compatible
Otto Chemie	Vitroflex N	Silicone	Neutral		Compatible
Pecora Corp.	AC-20 Silicone	Silicone	Neutral	4th quarter 15	Compatible
Pecora Corp.	864NST	Silicone	Neutral	2nd Quarter 11	Compatible
Pecora Corp.	890NST	Silicone	Neutral	2nd Quarter 11	Compatible
Pecora Corp.	895NST	Silicone	Neutral	2nd Quarter 11	Compatible
Pecora Corp.	896	Silicone	Neutral	2nd Quarter 11	Compatible
Pecora Corp.	896SSL	Silicone	Neutral	2nd Quarter 11	Compatible
Pecora Corp.	896HIS	Silicone	Neutral	2nd Quarter 11	Compatible
Pecora Corp.	1215	Silicone	Neutral	2nd Quarter 11	Compatible
Pecora Corp.	896TBS SSL	Silicone	Neutral	2nd Quarter 11	Compatible
Pecora Corp.	896TBS	Silicone	Neutral	2nd Quarter 11	Compatible
Permapack	Permabond 145	Silicone	Neutral		Compatible
Permapack	Permabond 145S	Silicone	Neutral		Compatible
Permapack	Permabond 153, grey	MS hybrid polymer	neutral		Compatible
Permapack	Permabond 153, grey	MS polymer	neutral		Compatible
Permapack	Permafex 153, transparent	MS hybrid polymer	neutral		Compatible
Pro Part	Klebe Dicht KD 385, black	MS polymer	neutral		Compatible
Pro Part	Klebe Dicht MS 380, transparent	MS polymer	neutral		Compatible
Pro Part	MS-Scheibenkleber MS390, black	Sylil Mod. Polymer	neutral		Compatible
Ramsauer	340, black	Silicone	neutral		Compatible
Ramsauer	350, white	Silicone	neutral		Compatible
Ramsauer	380, black	Silicone	neutral		Compatible
Ramsauer	Alkoxy 130, transparent	Silicone alkoxy	neutral		Compatible
Ramsauer	Glasleisten Fuller 490, rosa	Silicone alkoxy	neutral		Compatible
Ramsauer	Neutral 120, transparent	Silicone	neutral		Compatible
Reca	S 78, white	MS polymer	neutral		Compatible
Remmers	Albardin Multi-sil, white	Silicone alkoxy	neutral		Compatible
Remmers	Multi-SIL	Silicone	Neutral		Compatible
Remmers	Multisil GE1086, black	Silicone	neutral		Compatible
Rodhorsil	V60, transparent	Silicone	neutral		Compatible
Rotanium	Rotabond 2000, grey	MS Polymer	neutral		Compatible
Saarnova	Anschlusspaste	Silicone	Neutral		Compatible
SB-Chemie	SB-SIL-N, white	Silicone alkoxy	neutral		Compatible
Schnee-Morehead	7100 Permthane sealant	Polyurethane		1st Quarter 11	Compatible
Schnee-Morehead	cura sil SM2100	Elastomeric		1st Quarter 11	Compatible
Schnee-Morehead	SM7108	Polyurethane		1st Quarter 11	Compatible
Schnee-Morehead	SM5731	Silicone		1st Quarter 11	Compatible
Schnee-Morehead	SM5555	Acrylic		1st Quarter 11	Incompatible
Schnee-Morehead	SM5522	Acrylic		1st Quarter 11	Incompatible

" The Sealants have been conditioned for 4 weeks per the Rossenheim IFT Method. Fenzi formally advises its customers to use only "approved" products. It should be noted, however, that this list represents product combinations that have been successfully tested at one particular point in time. Fenzi can in no manner be held responsible for a possible change in chemical composition of a prior approved product made by another company. Fenzi regular customers can request compatibility tests at any time, service is free of charge."



LIST OF COMPATIBLE SEALANTS WITH THIOVER,

Fenzi North America
11 Dansk Court
Toronto, Ontario

HOTVER A+ AND BUTYLVVER

Phone: 416-674-3831
Fax: 416-674-9323

Schnee-Morehead	SM5504	Acrylic		1st Quarter 11	Incompatible
SCL Sterling	AquaGlaze	Latex water base		3rd quarter 10	Compatible
Selena USA	Tytan Professional WD20	Silicone	Neutral oxime	3rd quarter 10	Compatible
Selena USA	Tytan Pro Polyurethane foam	Polyurethane	neutral	2nd quarter 16	Compatible
Sika	Sikasil SG-15, black	Silicone	Neutral	4th quarter 11	Compatible
Sika	Sikaflex - 260, black	Polyurethan 1K	moisture		Compatible
Sika	Sikaflex 212 FC, black	Polyurethan 1K			Compatible
Sika	Sikaflex 252, white	Polyurethan 1K			Compatible
Sika	Sikaflex 552, black	Sil.Term. prepolymer	moisture		Compatible
Sika	Sikaflex 552, white	Silane Term. Prepolyme	moisture	2nd quarter 09	Compatible
Sika	Sikaflex 84UV	Polyurethan			Compatible
Sika	Sikasil IG-25 HM, black	Silicone	2K		Compatible
Sika	Sikasil IG-25, Grey	Silicone	2K	1st Quarter 12	Compatible
Sika	Sikasil IG-25, black	Silicone	2K		Compatible
Sika	Sikasil SG-20, black	Silicone	moisture		Compatible
Sika	Sikasil WS-605 S, black	Silicone	butanone-oxime		Compatible
Sika	Sikaflex Wt-480	Silicone alkoxy	2K Neutral	4th quarter '10	Compatible
Sika- Goessl Pfaff	Elastosil SG500, black	Silicone	2K		Compatible
Silco	Sil-Flex RTV 7500, white	Silicone	neutral	2nd quarter 08	Compatible
Soudal	Acryrub, black	Acrylate Dispersion	1K, acrylic		Compatible
Soudal	Fix All 05/06, light beige	MS hybrid polymer	neutral		Compatible
Soudal	Fix All 06/07, white	MS hybrid polymer	neutral		Compatible
Soudal	Fix All Crystal, transparent blue	MS polymer	neutral		Compatible
Soudal	Glaskit TS black	MS polymer	neutral		Compatible
Soudal	Glaskit TS, brown	MS polymer	neutral		Compatible
Soudal	Glaskit TS, grey	MS polymer	neutral		Compatible
Soudal	Soudaseal 240FC, grey	MS Polymer	neutral		Compatible
Soudal	Soudaseal 240FC, white	MS polymer	neutral		Compatible
Soudal	Soudaseal 4 all paint,white9001	MS polymer	neutral		Compatible
Soudal	Soudaseal 4 all paint,white9010	MS polymer	neutral		Compatible
Tenachem	Tenaglass-2, black	Polysulfide 2K	2K		Compatible
Torggler	Sitol Silicon, black	Silicone	neutral		Compatible
Tremco	Butyl	Butyl		3rd quarter 10	Compatible
Tremco	Dymonic	Polyurethane		3rd quarter 10	Compatible
Tremco	Dymonic FC	Low M. P.U		3rd quarter 10	Compatible
Tremco	Spectrem-2	Med. M. silicone		3rd quarter 10	Compatible
Tremco	Spectrem-2	Med. M. silicone		2nd quarter 16	Compatible
Tremco	Tremsil 600	Med.M. Silicone		1st quarter 12	Compatible
Tremco	Proglaze SSG, Black	Silicone	neutral	1 quarter 09	Incompatible
Tremco	Tremco 200	Butyl		2nd quarter 14	Incompatible
Tremco	Tremsil 600	Silicone	Neutral	3rd quarter 16	Compatible
Tremco	Tremco 830, Clear	butyl		2nd quarter 14	Incompatible
Tremco	Tremflex 834	acrylic latex	1k, acrylic	1st quarter 08	Compatible
Tremco	Tremglaze S500	Silicone	Neutral	3rd quarter 16	Compatible
Tremco	Tremco 830, White	Butyl		2nd quarter 14	Incompatible
Tremco - Illbruck	Perennator FA 101, black	Silicone	neutral		Compatible
Wacker	Elastosil SG20, black	Silicone			Compatible
Wacker	Elastosil SG500, black	Silicone	neutral, 2K		Compatible
Weicon	Flex 310 M, black	POP hybrid polymer			Compatible
Weicon	Speed-Flex, grey		neutral		Compatible
Wicona	Wic Pro Klebstoff, light brown	Polyurethan 2K			Compatible
Wisabax AG	SK 900, transparent blue	Kautschuk 1K	vulcanization		Compatible
Würth	saBesto, dark brown	Silicone	neutral		Compatible
Würth	saBesto, transparent	Silicone	neutral		Compatible
Würth	saBesto, transparent white	Silicone	neutral		Compatible
Zweygart	Roccasol 230, black	Silicone	neutral		Compatible
Zweygart	Roccasol 230, transparent	Silicone	neutral		Compatible
3M	Hybrid Adhesive Sealant Fast Cure 4000 UV	Fast Cure PU	neutral	4th quarter 16	Compatible

List as of Jan 18

" The Sealants have been conditioned for 4 weeks per the Rossenheim IFT Method. Fenzi formally advises its customers to use only "approved" products. It should be noted, however, that this list represents product combinations that have been successfully tested at one particular point in time. Fenzi can in no manner be held responsible for a possible change in chemical composition of a prior approved product made by another company. Fenzi regular customers can request compatibility tests at any time, service is free of charge."